

--21. (New) The polyamic acid of claim 2, of which the inherent viscosity measured in a solvent of N-methyl-2-pyrrolidone having the acid concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.

A2 22. (New) The polyamic acid of claim 1, of which the inherent viscosity measured in a solvent of N-methyl-2-pyrrolidone having the acid concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.

23. (New) The polyimide of claim 5, of which the inherent viscosity measured in a mixed solvent of p-chlorophenyl/phenol = 9/1 (by weight) having the polyimide concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.

24. (New) The polyimide of claim 4, of which the inherent viscosity measured in a mixed solvent of p-chlorophenyl/phenol = 9/1 (by weight) having the polyimide concentration of 0.5 g/dl at 35°C falls between 0.1 and 3.0 dl/g.--

---